

Test Report



Report No. A223036704410100103

Page 1 of 4

Company Name
Shown on Report SHENZHEN JDB TECH. CO. LTD.Address ROOM 1105-1108, NO.2 BUILDING, EST MALL BUSINESS CENTER,
NO.698 CHANGBANG ROAD, XIACHENG DISTRICT, 310004,
HANGZHOU, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name	2layers PCB
Material	pcb
Sample Received Date	Jul. 24, 2023
Testing Period	Jul. 24, 2023-Aug.2, 2023

Test Requested

No.	Test Item
1	Bond strength

Test Result(s): Please see the following pages.Approved by Annie LangDate Aug. 18, 2023

No. RDAAD41CF3

Test Report

Report No. A223036704410100103

Page 2 of 4

Tested Sample(s)

Sample No.	Sample Name	Material
A2230367044101001	2layers PCB	pcb

Sample Photo(s)



A2230367044101001



Test Report

Report No. A223036704410100103

Page 3 of 4

Test Item: Bond strength**1. Test Equipment**

Equipment Name	Model
Microcomputer control testing machine	ETM501B

2. Environmental Conditions

Temperature: 23.5℃; Humidity: 49% RH

3. Test Standard: IPC-TM-650 2.4.21F**4. Test Conditions**

Sample status: receiving state. Test speed: 50mm/min

5. Test Result(s)

Test Sample		Test Results (N)
A2230367044101001	1	183.58
	2	205.25
	3	239.57
	4	185.33
	5	250.66
	6	229.65
	7	198.02
	8	197.43
	9	226.54
	10	194.01

Test Report

Report No. A223036704410100103

Page 4 of 4

Remark: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Statement:

- 1.This report is considered invalid without approved signature, special seal and the seal on the perforation;
- 2.Company Name and Address shown on Report, the sample(s) and sample Information was/were provided by the applicant who should be responsible for the authenticity which CTI hasn't verified;
- 3.The result(s) shown in this report refer(s) only to the sample(s) tested;
- 4.Without written approval of CTI, this report can't be reproduced except in full;
- 5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** End of Report ***

